

EMC53-1

Polyurethane: Moisture Cured, Solvent-Based, Aromatic Polyether

PRODUCT DESCRIPTION

LOW VOC MEETS 350 g/l STANDARDS

EMC53-1 is an aromatic oil free, one-package, moisture cured, polyurethane resin used to develop high gloss coatings for wood, concrete and metal substrates. **EMC53-1** cures by the reaction of available NCO with moisture in the ambient environment, resulting in a coating with exceptional durability.

APPLICATIONS

- --Hardwood Floors
- --Concrete Topcoats over epoxy surface)
- -- Metal Protective Coats

STORAGE AND HANDLING:

EMC53-1 is a moisture cure, NCO terminated material as such, any opened container which is exposed to moisture will increase in viscosity, gel and/or become solid. If moisture is introduced, use the product immediately. Any container, once opened, should be resealed with a nitrogen blanket. EMC53-1 should be applied at temperatures greater than 50°F. EMC53-1has a shelf life of 6 months.

| TECHNICAL INFORMATION | | Typical Physical Properties |
|-----------------------|----------------------|--|
| Solids | 40-43 . = | o , |
| NCO | 2.7 - 3.3 | Elongation 5 |
| Weight/Gallon | .24 lb/gal | Hardness Sward) 3 |
| Viscosity | @ 25°C) 50 - 100 cps | Tensile Strength 5000 psi |
| Color | Clear | Impact resistance direct)160 inch pounds |
| VOC g/I | 。350 | reverse)140 inch pounds |

CAUTION EMC53-1 contains flammable liquids. KEEP AWAY FROM HEAT, SPARKS AND FIRE. Do not leave container open. Use with adequate ventilation. Avoid prolonged or repeated breathing of vapor or repeated or prolonged contact of liquid with skin.

ASTM TEST METHODS

Solids - D-236 Hardness - D-2134 Viscosity - D-21 6 Tensile - D-412 Abrasion - D-4060 Wt./Gallon - D-1475 Elongation - D-412 VOC Properties D-3 60

¹Taber Abrasion Weight Loss 1000 gram load/1000 cycles

²Instron tester films pulled at 2 inches per minute